

SPIRALI IN POLIAMIDE SENZA CODOLI

SPIRALS POLYAMIDE WITHOUT TANGS
 SPIRALROHRE AUS POLYAMID OHNE GERADE ENDEN
 TUBE SPIRALÉ EN POLYAMIDE SANS EXTRÉMITÉS DROITES
 ESPIRALES EN POLIAMIDA SIN TERMINALES
 ESPIRAIS DE POLIAMIDA SEM ABAS

SS12

SPIRALE IN POLIAMIDE SENZA CODOLI

POLYAMIDE SPIRAL WITHOUT TANGS

SPIRALROHRE AUS POLYAMID OHNE GERADE ENDEN

TUBE SPIRALÉ EN POLYAMIDE SANS EXTRÉMITÉS DROITES

ESPIRAL EN POLIAMIDA SIN TERMINALES

ESPIRAL DE POLIAMIDA SEM ABAS



| Code | Colore Color Farbe Couleur Color Cor | Est. | Int. | Ø Est. | Lunghezza Lineare Linear Length Gerade Länge Longueur Étirée Longitud Lineal Comprimento Linear | Pressione d'esercizio Working pressure Betriebsdruck Pression de travail Presión de ejercicio Pressão de trabalho | | Pressione di scoppio Burst pressure Berstdruck Pression d'éclatement Presión de rotura Pressão de ruptura | | Pack. |
|---------------|---|------|------|--------|--|--|------------------|--|------------------|-------|
| | | | | | | a/at 20°C bar | a/at 20°C bar | a/at 20°C bar | a/at 20°C bar | |
| SS12 0064 030 | BL | 6 | 4 | 63 | Mt | 27 | 81 | 1 | | |
| SS12 0086 030 | BL | 8 | 6 | 87 | Mt | 20 | 60 | 1 | | |
| SS12 0108 030 | BL | 10 | 8 | 106 | Mt | 15 | 45 | 1 | | |
| SS12 0121 030 | BL | 12 | 10 | 135 | Mt | 13 | 39 | 1 | | |



Temperatura d'uso

Temperature Range

Temperaturbereich



Température d'utilisation

Temperatura de Ejercicio

Temperatura de Trabalho

- 40 °C

+ 70 °C

Tabella delle pressioni espresse in % in funzione della temperatura
 Table of pressure values expressed in% as a function of temperature
 Tabelle In Abhängigkeit Der Temperaturen Die Druckwerte In % Angegeben
 Valeurs de pression (en %) en fonction de la température
 Tabla de las presiones expresadas en % en función de la temperatura
 Tabela das pressões expressas em % em função da temperatura

| -20° | 0° | 20° | 30° | 40° | 50° | 60° | 70° |
|------|------|------|-----|-----|-----|-----|-----|
| 180% | 140% | 100% | 90% | 80% | 70% | 60% | 50% |