

TUBO IN POLIURETANO POLIESTERE 98 SHORE A

98 SHORE A POLYURETHANE POLYESTER TUBE
 ROHRE AUS POLYURETHAN-POLYESTER 98 SHORE A
 TUBE EN POLYURÉTHANE POLYESTER 98 SHORE A
 TUBO EN POLIURETANO POLIÉSTER 98 SHORE A
 TUBO DE POLIURETANO POLIÉSTER 98 SHORE A

TBPU

TUBO IN POLIURETANO POLIESTERE 98 SHORE A

98 SHORE A POLYURETHANE POLYESTER TUBE
 ROHRE AUS POLYURETHAN POLYESTER 98 SHORE A
 TUBE EN POLYURÉTHANE POLYESTER 98 SHORE A
 TUBO EN POLIURETANO POLIÉSTER 98 SHORE A
 TUBO DE POLIURETANO POLIÉSTER 98 SHORE A



Code	Colore Color Farbe Couleur Color Cor						Est. mm	Int. mm	Raggio di curvatura Bending radius Biegeradius Rayon de courbure Radio curvatura Raio de curvatura mm	Pressione d'esercizio Working pressure Betriebsdruck Pression de travail Presión de ejercicio Pressão de trabalho a/at 20°C bar	Pressione di scoppio Burst pressure Berstdruck Pression d'éclatement Presión de rotura Pressão de ruptura a/at 20°C bar	Pack. Mt
	White	Blue	Black	Yellow	Red	Diagonal						
TBPU 00 425	NT	AZ	NE	-	RO	TT	4	2.5	15	10	40	100
TBPU 00 530	NT	AZ	NE	-	-	-	5	3	16	12	50	100
TBPU 00 640	NT	AZ	NE	GI	RO	TT	6	4	18	10	40	100
TBPU 00 855	NT	AZ	NE	-	RO	TT	8	5.5	30	10	40	100
TBPU 00 860	NT	AZ	NE	-	RO	TT	8	6	35	8	32	100
TBPU 01 080	NT	AZ	NE	-	RO	TT	10	8	45	5.5	22	100
TBPU 01 290	NT	AZ	NE	-	RO	TT	12	9	50	6	25	100

TSPU

TUBO IN POLIURETANO POLIESTERE 98 SHORE - LUNGHEZZA 25 Mt

98 SHORE A POLYURETHANE POLYESTER TUBE - LENGHT 25 Mt
 ROHRE AUS POLYURETHAN POLYESTER 98 SHORE A - LÄNGE 25 Mt
 TUBE EN POLYURÉTHANE POLYESTER 98 SHORE A - ROULEAU DE 25 Mt
 TUBO EN POLIURETANO POLIÉSTER 98 SHORE A - LONGITUD 25 Mt
 TUBO DE POLIURETANO POLIÉSTER 98 SHORE A - COMPRIMENTO DE 25 Mt



Code	Colore Color Farbe Couleur Color Cor			Est. mm	Int. mm	Raggio di curvatura Bending radius Biegeradius Rayon de courbure Radio curvatura Raio de curvatura mm	Pressione d'esercizio Working pressure Betriebsdruck Pression de travail Presión de ejercicio Pressão de trabalho a/at 20°C bar	Pressione di scoppio Burst pressure Berstdruck Pression d'éclatement Presión de rotura Pressão de ruptura a/at 20°C bar	Pack.
	White	Blue	Black						
TSPU 00 425	NT	AZ	NE	4	2.5	15	10	40	1
TSPU 00 640	NT	AZ	NE	6	4	18	10	40	1
TSPU 00 855	NT	AZ	NE	8	5.5	30	10	40	1
TSPU 00 860	NT	AZ	NE	8	6	35	8	32	1
TSPU 01 080	NT	AZ	NE	10	8	45	5.5	22	1
TSPU 01 290	NT	AZ	NE	12	9	50	6	25	1



Temperatura d'uso

Temperature Range

Temperaturbereich

Température d'utilisation

Temperatura de Ejercicio

Temperatura de Trabalho



- 40 °C

+ 60 °C

Tabella delle pressioni espresse in % in funzione della temperatura
 Table of pressure values expressed in% as a function of temperature
 Tabelle In Abhängigkeit Der Temperaturen Die Druckwerte In % Angegeben.
 Valeurs de pression (en %) en fonction de la température
 Tabla de las presiones expresadas en % en función de la temperatura
 Tabela das pressões expressas em % em função da temperatura

-20°	0°	20°	30°	40°	50°	60°
185%	140%	100%	85%	70%	60%	50%